



GRIP SHEET 90 TECHNICAL INFORMATION

CHARACTERISTICS	UNIT	MIDDLE VALUE	OBSERVATION	TRIAL REFERENCE
PAPER QUALITY	Gr / sqm	90		
WEIGHT OF TREATMENT	Gr / sqm	25		
TOTAL WEIGHT	Gr / sqm	115	“-5 / +5 g	
KIND OF COMPOUND			ATOCHEM compound	
MELTING POINT	Degrees C	120		NFT 60121
FLASH POINT	Degrees C	296		NFT 60118
COLOUR		0.5		NFT 60104
ODOUR	Astm	0		D 1853
TOXIC EFFECTS (ORAL OR SKIN)			NONE	
RECYCLABLE			YES	
BIODEGRADABLE			YES	
SUITABLE FOR DIRECT CONTACT WITH FOOD PRODUCTS			YES	LNE Trial of the 11 th of June 96

*** Pallets of 3,500 Sheets

*** Delivery Time: 2 Weeks

*** Storage: Tolerates all temperatures between -30°C and + 65°C
There is no noticeable degradation with passage of time.

*** Waterproof Quality Available

ENDUPACK SA